

## PMR Flex Primer

Description	A rapid drying flexible primer. Suitable for covering minor blemishes scratches etc. Can be overcoated with solvent and water borne paints. Resistant to spills of petrol and diesel. Suitable for sanding down after drying with wet or dry sandpaper.
Recommended Use	Suitable for application to ferrous and non-ferrous metal surfaces on vehicle components, agricultural and construction equipment.
Composition	Pigmented acrylic resins.
Specific Gravity	Approx 1.25 - 1.30 as paint
Solids	Weight : approx 51% Volume : approx 31%
Finish	Matt.
Flash Point	27°C
Drying Time @ 20°C	Surface dry - 10 mins. Hard dry - 20 mins. Overcoatable after 20 minutes. Drying times will be extended at low temperatures and high film thicknesses. Do not apply when ambient temperature falls below 3°C or relative humidity exceeds 90%.
Packaging	Variable
Colour Range	Clear (can be Coloured)
Directions for end users	Ensure all surfaces are clean, dry and free from dust, grease, millscale, etc. Mix well before use. Bright surfaces should be sanded to provide a suitable key. When applying over previously painted surfaces apply a test patch to check compatibility. For further information contact our Technical Service Department.